

High Pressure Laminate



Three standard grades of **Nevamar® High Pressure Laminate** are suitable for most applications:

General Purpose Type NG48 is most often used in horizontal applications where high impact resistance and a durable, decorative surface is required.

Postforming Type NF39 is designed for manufacturing countertops and other horizontal surfaces where the laminate may be heated and rolled over the substrate edge to eliminate seams.

Type NF28 is designed for applications where impact resistance is less critical. Type NF28 can also be postformed.

Product Description

High pressure laminate is manufactured in a flat press by combining decorative papers saturated in melamine resin with phenolic-impregnated kraft layers at pressures exceeding 1000 psi (6.9 MPa) and temperatures approaching 300°F (150°C). The panels are trimmed to size and the backs are sanded to facilitate bonding. The thickness of the laminate is determined by the number of kraft layers used. The laminating process combines the durability of melamine resins with the aesthetics of decorative papers creating a surfacing material that has been the standard for many years.

Most textured finish items are produced with Nevamar's exclusive **Armored Protection® Surface** and have all the properties of conventional laminate. But it also has superior abrasion and scuff resistance due to a very thin deposit of microscopic particles of aluminum oxide on the conventional melamine layer. Armored Protection® Surface has significantly better wear value than the NEMA standard for laminates. It also offers superior resistance to scuffing and retain a "brand new" appearance during most of their useful life. All other properties meet the normal NEMA test requirements. Nevamar HPL is also available in an integral antimicrobial finish designed to protect the decorative surface from discoloration and odors caused by a variety of microorganisms.

Standard Nominal Sizes

Type	Thickness*	Width*	Length	Colors
NG48 (mm)	0.045 ± 0.005 1.14 ± 0.13	36, 48, 60 914, 1219, 1524	96, 120, 144 2438, 3048, 3658	All solids, patterns & woodgrains
NF39 (in.) (mm)	0.036 ± 0.005 0.91 ± 0.13	36, 48, 60 914, 1219, 1524	96, 120, 144 2438, 3048, 3658	All solids, patterns & woodgrains
NF28 (in.) (mm)	0.028 + 0.001 - 0.004 0.71 + 0.03 - 0.10	36, 48, 60 914, 1219, 1524	96, 120, 144 2438, 3048, 3658	All solids, patterns & woodgrains

*Other widths and thicknesses available upon request.

Typical Uses

Nevamar® standard laminate is designed for either horizontal, vertical, or postforming applications. This laminate is seen on countertops, tables, vanities, interior doors, cabinets, contract furniture, and retail store fixtures.

Fabrication Tips

When working with Nevamar® HPL, these techniques will produce a quality application.

1. Proper conditioning of the laminate, substrate, and backing sheet minimizes possible warping, shrinking, or expansion of assembled panels. Ideally, all components should be conditioned at 70°F to 75°F (21°C to 25°C) and 45 to 50 percent relative humidity for 48-hours prior to assembly.
2. Always bond laminate to a suitable substrate such as medium to high density fiberboard, particleboard, or metals. It should not be glued directly to plaster walls, gypsum wallboard, or concrete.
3. Recommended adhesives include solvent or water-based contact cement, white glue (PVA), epoxy, and hot melt glue. Consult your adhesive supplier for specific application requirements.
4. The use of a backing sheet is recommended to minimize warpage. The thickness of the backing sheet should be relatively equal to the thickness of the decorative laminate on the face of the assembly.
5. All saw blades and router bits used for cutting should be carbide tipped. Feed rate should be slow and tool speed should be high.

6. All edges of laminate should be filed smooth with file direction towards substrate to help prevent stress cracks and to minimize chipping.
7. Inside corners of cutouts for electrical outlets, sinks, etc., should have a minimum radius of 1/8" (3 mm) and be filed smooth. This reduces the likelihood of stress cracks.
8. When fasteners are required, it is advisable to first drill an oversized hole through the laminate. This reduces the likelihood of stress cracks.
9. See the Nevamar® Postforming Technical Bulletin for postforming application tips.
10. All laminate is intended for interior use only, and should not be exposed to extreme humidity, continuous sunlight, or temperatures above 275°F (135°C) for extended periods of time.

Fire Test Data

High pressure decorative laminate is frequently used in installations governed by local fire codes. Burning characteristics of laminate are greatly influenced by the adhesive and substrate used. Listed below are typical flame spread index and smoke developed values for Nevamar® standard grade laminate. When specifying Class I or A rated laminate, refer to Nevamar® Fire Rated Technical Bulletin.

CAN/ULC-S102M

Laminated Plastic Surface Burning Characteristics

Type	Configuration	Flame Spread Index	Smoke Developed Values
NG48	Bonded* to	155	35
NF39	Inorganic	45	20
NF28	Cement Board	35	10

*Bonded with N® Sodium Silicate Sealer and Wonderbond® WB-104A with M-172L. All work should be designed, assembled, and installed in compliance with pertinent local fire codes.

Technical Information

Physical Properties

		NEMA LD 3-2005 TEST Method	TYPICAL NEVAMAR® VALUES NG48	NEMA STD. HGS	TYPICAL NEVAMAR VALUES NF39	NEMA STD. HGP	TYPICAL NEVAMAR® VALUES F28	NEMA STD. VGP
Thickness	(in.) (mm)		0.045 ± 0.005 1.14 ± 0.13		0.036 ± 0.005 0.91 ± 0.13		0.028 + 0.001 - 0.0040 0.71 + 0.03 - 0.10	
Appearance		3.1	Complies		Complies		Complies	
Light Resistance		3.3	no effect	Slight effect	no effect	Slight effect	no effect	Slight effect
Cleanability		3.4	7-11	20 (max)	7-10	20 (max)	7-10	20 (max)
Stain 1-10			No effect	No effect	No effect	No effect	No effect	No effect
Stain 11-15			No effect	Moderate effect	No effect	Moderate effect	No effect	Moderate effect
Boiling Water Resistance		3.5	No effect	No effect	No effect	Slight effect	No effect	Slight effect
High Temperature Resistance		3.6	No effect	Slight effect	No effect	Slight effect	No effect	Slight effect
Ball Impact Resistance	(in.) (mm)	3.8	66 1676	50 (min.) 1250 (min.)	48 750 (min.)	30 (min.) 750 (min.)	40 1016	20 (min.) 500 (min.)
Radiant Heat Resistance	(sec)	3.10	300	125 (min.)	275	100 (min.)	250	80 (min.)
Dimensional Change		3.11						
Machine Direction	(%)		0.35	0.50 (max.)	0.35	1.1 (max.)	0.35	1.1 (max.)
Cross Direction	(%)		0.75	0.90 (max.)	0.75	1.4 (max.)	0.75	1.4 (max.)
Room Temperature Dimensional Stability		3.12						
Machine Direction	(%)		0.30	0.5 (max.)	0.25	1.0 (max.)	0.30	1.0 (max.)
Cross Direction	(%)		0.50	0.8 (max.)	0.45	1.3 (max.)	0.60	1.3 (max.)
Wear Resistance	(cycles)	3.13	1000	400 (min.)	1000	400 (min.)	1000	400 (min.)
Formability	(in) (mm)	3.14	Not applicable	Not applicable	3/8 10	5/8 (min.) 16 (min.)	1/4 7	1/2 (min.) 13 (min.)
Blister Resistance	(sec)	3.15	Not applicable	Not applicable	60	55 (min.)	52	40 (min.)

ASTM E-84/UL723
“Standard Test Method for Surface Burning
Characteristics of Building Materials”

Type	Sample Configuration	Flame Spread Index	Smoke Developed Values
NG48	Unbonded	40	120
NF39		40	65
NF28		35	35
NG48	Bonded* to	55	85
NF39	Inorganic	55	105
NF28	Cement Board	35	40
NG48	Bonded* to 5/8"	95	95
NF39	Particleboard	235	140
NF28		160	160
NG48	Bonded* to 5/8"	160	110
NF39	Fire Rated	110	130
NF28	Particleboard	80	75

*Bonded with Pioneer P19NF contact cement. All work should be designed, assembled and installed in compliance with pertinent local fire codes.

Codes and Certifications

1. U.S. Federal Motor Vehicle Safety Standard #302 “Flammability of Interior Materials.” Nevamar® Type NG48, NF39, and NF28 comply.
2. NSF-International Standard 35, “Laminated Plastics for Surfacing Food Service Equipment.” Nevamar® Type NG48, NF39, and NF28 comply.
3. American National Standards Institute/National Electrical Manufacturers Association (ANSI/NEMA), LD3-2005, “High- Pressure Decorative Laminate.” Nevamar® Type NG48, NF39, and NF28 comply.
4. MIL-P-17171E(SH), “High Pressure Decorative Laminate.” Nevamar® NG48 complies with Type I.
5. U.S. Federal Specification L-P-508H, “Plastic Sheet, Laminated, Decorative and Nondecorative.” Nevamar® Type NG48, NF39, and NF28 comply.
6. International Organization for Standardization, ISO-4586, “Decorative High Pressure Laminates (HPL).” Nevamar® Type NG48, NF39, and NF28 comply.

Care and Maintenance

Nevamar® decorative laminate provides a durable surface that is easy to maintain using ordinary care.

To maintain the laminate’s lasting beauty, cleaning with a solution of warm water and liquid dishwashing detergent is all that should be required in most cases.

Stains may be removed with most non-abrasive household cleaners such as FORMULA 409®, GLASS PLUS® or WINDEX® with AMMONIA D®. Light scrubbing with a soft bristled brush may be necessary to remove

stains from the depth of the structure on some textured surfaces.

If the stain persists, use a paste of baking soda and water and apply with a soft bristled brush. Light scrubbing for 10-20 strokes should remove most stains. Although baking soda is a low abrasive, excessive scrubbing or exerting too much force may damage the decorative surface, especially if it has a gloss finish.

Stubborn stains that resist any of the above cleaning methods may require the use of undiluted household bleach. Apply the bleach to the stain and let stand no longer than 1 1/2 minutes. Rinse thoroughly with warm water and wipe dry. This step may be repeated if the stain appears to be going away and the color of the laminate has not been affected. WARNING: Prolonged exposure of the laminate surface to bleach will cause discoloration.

Many commercially available products contain substances that may damage or discolor a laminate surface. ABRASIVE CLEANERS SHOULD NOT BE USED. Particular care should be used with any products labeled CAUTION or WARNING. Any questions or concerns should be referred to the product’s manufacturer or call 1-877-726-6526. Do not allow harsh materials to remain in contact with the laminate surface. Examples of these are as follows:

- Toilet bowl cleaners
- Chlorine bleach
- Hydrogen Peroxide
- Coffee pot cleaners
- Oven cleaners
- Hard water stain removers
- Drain cleaners
- Fruit and berry juice
- Metal cleaners and polishes
- Tub and tile cleaners

Formula 409 is a registered trademark for The Clorox Company of Oakland, CA 94612; Glass Plus is a registered trademark for The Dow Chemical Company of Indianapolis, IN 46268-0511; Windex is a registered trademark for S.C. Johnson & Sons INC. of Racine, WI 53403-5011.

Limited Warranty

Subject to the limitations set forth below, Panolam Industries International Inc. (Panolam) expressly warrants that our products are reasonably free of defects in material and workmanship, and when properly handled and fabricated will conform, within accepted tolerances, to applicable manufacturing specifications as set forth in our technical brochure. This warranty shall extend to the original buyer for a period of twelve (12) months from the date of shipment of this product by Panolam, and shall not be assignable by the original buyer. This warranty does not cover damage resulting from accident, misuse, alteration, abuse or lack of reasonable care.

Due to the variety of uses and applications to which this product may be put, and because the manufacturer has no control over the end products fabricated, the warranty set forth above is exclusive and in lieu of all warranties, expressed or implied, in fact or by operation of law or otherwise, or arising by course of dealing or performance, custom or usage in the trade, including, without limitation, the implied warranties of fitness for a particular purpose and merchantability, and Panolam shall have no obligation or liability to any person or entity in connection with or arising from the furnishing, sale, installation or repair, use or subsequent sale of any product supplied by it.

Our maximum liability arising out of the sale of the products or their use, whether based upon warranty, contract, tort or otherwise, shall not exceed the actual payments received by us in connection therewith.

In no event shall we be liable for special, incidental or consequential damages, including, but not limited to, arising hereunder or from the loss of profits, or loss of use damages, sales of the products.

Headquarters

Panolam Industries International, Inc.

2 Corporate Drive, Suite 946

Shelton, CT 06484

1-877-726-6526

www.panolam.com



© 2024 Panolam Industries International, Inc.

5/2024