



Product Identification

Grade: Conolite® 6100T Series Cargo Liners

Conolite® 6100T Series represents the most advanced selection of fiberglass reinforced phenolic cargo liners. Conolite® 6100T exhibits the low smoke and toxicity inherent in phenolic resins. The modified phenolic resin combined with the careful selection of “S-2” woven fiberglass reinforcements, create the highest strength to weight ratio of any commercial cargo liner available today.

Specification

Conolite® Cargo Liners meet or exceed the following material specifications:

Boeing BMS 8-223, Class 4, Grade B

Technical Data (nominal values)

| Property | | Product Description | | | |
|--------------------------|-----------------------|--|---------------|---------------|---------------|
| | | 6100T.013 | 6100T.020 | 6100T.030 | 6100T.040 |
| Thickness | (in.) | 0.011 ± 0.003 | 0.017 ± 0.003 | 0.024 ± 0.003 | 0.035 ± 0.004 |
| Max Weight | (lb/ft ²) | 0.106 | 0.165 | 0.245 | 0.33 |
| Drum Peel | | | | | |
| Warp | (in-lb/3 in) | NA | 22 | 20 | 20 |
| Fill | (in-lb/3 in) | NA | 42 | 38 | 44 |
| Edge Bearing | | | | | |
| Warp | (psi) | 34,700 | 37,700 | 41,000 | 43,000 |
| Fill | (psi) | 34,100 | 38,400 | 40,000 | 44,000 |
| Impact Strength (ft lbs) | | | | | |
| BSS 7326 | Method 1 | 9 | 14 | 16 | 23 |
| | Method 2 | 11.6 | 17.4 | 23.8 | 29.5 |
| Flame Spread Index | | 3 | 2.4 | 3.4 | 3.9 |
| Smoke Density | | 14 | 19 | 21 | 23 |
| Flammability | | Meets requirements of FAR 25, Appendix F, Part III. FAA 8110-3 available for all liners. | | | |

Limited Warranty

Subject to the limitations set forth below, Panolam® Industries International Inc. (Panolam) expressly warrants that our products are reasonably free of defects in material and workmanship, and when properly handled and fabricated will conform, within accepted tolerances, to applicable manufacturing specifications as set forth in our technical brochure. This warranty shall extend to the original buyer for a period of twelve (12) months from the date of shipment of this product by Panolam, and shall not be assignable by the original buyer. This warranty does not cover damage resulting from accident, misuse, alteration, abuse or lack of reasonable care.

Due to the variety of uses and applications to which this product may be put, and because the manufacturer has no control over the end products fabricated, the warranty set forth above is exclusive and in lieu of all warranties, expressed or implied, in fact or by operation of law or otherwise, or arising by course of dealing or performance, custom or usage in the trade, including, without limitation, the implied warranties of fitness for a particular purpose and merchantability, and Panolam shall have no obligation or liability to any person or entity in connection with or arising from the furnishing, sale, installation or repair, use or subsequent sale of any product supplied by it.

Our maximum liability arising out of the sale of the products or their use, whether based upon warranty, contract, tort or otherwise, shall not exceed the actual payments received by us in connection therewith. In no event shall we be liable for special, incidental or consequential damages, including, but not limited to, arising hereunder or from the loss of profits, or loss of use damages, sales of the products.

Headquarters

Panolam® Industries International, Inc.
2 Corporate Drive, Suite 946
Shelton CT, 06484
www.panolam.com

Manufactured by

Pioneer Plastics
a division of Panolam® Surface Systems
325 Desoto Avenue
Morristown, TN 37814
1-877-726-6526
conolite_sales@panolam.com

